



Initial permeability	$\mu_i$	25°C	4000±25%
Saturation magnetic flux density	Bs(mT)	25°C	430
flux density	1194A/m	100°C	270
Remanent flux	Br(mT)	25°C	80