



Initial permeability	μ_i	25°C	1800±25%
Saturation magnetic flux density	$B_s(T)$	25°C	520
Remanence	$B_r(mT)$	100°C	430
Coercivity	$H_c(A/m)$	25°C	13
Core loss	$P_{c}(kW/m^3)$	25°C	900
		100kHz 200mT	500
		140°C	400



(A/m)

Frequency(kHz)

H

